# **Technical Data**

Issue 1 October 2003

## AT202 Gloss Cloth Gaffa Tape

#### **General description**

A gloss polycloth extruded tape with a white pressure sensitive, aggressive adhesive.

- Gloss finish
- Easy unwind
- Very easy tear
- Cable friendly, clean peel adhesive
- Wide colour range
- Can be written on
- Wide temperature range
- Water resistant in situ
- Good abrasion resistance
- Conformable to awkward shapes
- Non-corrosive adhesive

### **Technical Details**

Typical values

| Thickness                       |   | 0.22mm  |
|---------------------------------|---|---|
| Breaking Load                   |   | 33 N/cm   |
| Elongation                      |   | 13%   |
| Adhesior                        | n<br>Steel<br>Self                          | 5.5 N/cm<br>3.5 N/cm  |
| Moisture Vapour<br>Permeability |   | 20g/m²/24 hrs   |
| Water E                         | xtract<br>pH<br>ChlorideMax<br>Sulphate Max | 6.0 to 8.0<br>0.01% as NaCI<br>0.01% as Na <sub>2</sub> SO <sub>4</sub> |
| Service Temp                    |   | -50°C to +80°C  |
| Application Temp                |   | +10°C to +45°C  |



| NOTE  |
|---|
| Except where indicated otherwise, the above figures are     |
| average values and should not be regarded as MAXIMUM        |
| or MINIMUM values for specification purposes. The           |
| Company reserves the right to improve products and any      |
| change in specification will result in a re-issue of the    |
| relevant 'Technical Data Sheet'.Customers should satisfy    |
| themselves that the tape is suitable for their requirements |
| whether after such modifications or otherwise. Please       |
| check that you have the latest issue of the 'Technical Data |
| Sheet'.All slitting and length tolerances are to British    |
| Standards.Before use the customer is advised to consult     |
| the Health & Safety Data Sheet produced by the company      |
| for this product, which is available on request.            |
| STORAGE   |
| Tapos stored below the minimum recommended tempera          |

Tapes stored below the minimum recommended temperature will require warming up to that level before use. Up to 24 hours may be required for this to take place.





Advance Tapes International Limited, PO Box 122, Abbey Meadows, Leicester, LE4 5RA. Tel: 0116 251 0191. Fax: 0116 265 2046. www.advancetapes.com

#### **AFERA** Association des Fabricants Européens de Rubans Auto-Adhésifs.